



## ACID#8 1 LITER

### Ready to Use Etch Primer

<b>Description</b>	<p><b>ACID#8</b> is a 1K ready to use etch primer available in 1 liter cans. It is used for priming bare metal surfaces, this promotes adhesion of paint and prevents steel from rusting.</p> <p><b>ACID#8</b> is chromate free. Typical applications are over rub through areas prior to painting, on new bare metal panels or over bare seams before sealant is applied.</p>
<b>Surface preparation and instructions for use</b>	<p><b>ACID#8</b> can be applied to the following surfaces:-</p> <ul style="list-style-type: none"><li>• Bare steel.</li><li>• Aluminium.</li><li>• Galvanized and Zinc coated steels.</li><li>• Fully cured paint.</li><li>• Polyester bodyfillers and G.R.P.</li></ul> <p>Thoroughly clean and degrease surfaces with a suitable spirit wipe or thinner, like U-POL S2000, S2001, or S2002. Abrade wet or dry with 280–320 abrasive. Re-clean, dry, and degrease.</p>
<b>Health and Safety Statement</b>	<p>FOR PROFESSIONAL USE ONLY. Read full instructions before use.</p> <p>IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at <a href="http://WWW.U-POL.COM">WWW.U-POL.COM</a>. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment</p>
<b>Application and Storage information</b>	<p>Stir can thoroughly before use for a minimum of 2 minutes.</p> <p>Apply 1-2 light even coats.</p> <p>Allow 3-5 minutes flash off time between coats.</p> <p>The product can be thinned up to 5% with alcohol, e.g. IMS/Butanol.</p> <p>Equipment can be cleaned with an alcohol based thinner.</p>
<b>Drying Time</b>	<p>Allow 10-20 minutes before overcoating.</p> <p>Drying time is dependent upon film thickness, humidity and temperature</p>
<b>Overpainting</b>	<p>Under normal circumstances it is not necessary to flat <b>ACID#8</b> and can be directly overcoated.</p> <p><b>ACID#8</b> may be overcoated directly with top coat.</p> <p>However, if the repair requires additional build primer filler should be used before topcoat is applied.</p>
<b>VOC information</b>	<p>Regulatory: 5.90 lb/gal</p> <p>Actual: 5.90 lbs/gal</p>
<b>Product Code</b>	UP07776 – 1 Liter Can: Gray

### ACID#8 - MIR AEROSOL NOW AVAILABLE!

U-POL US, Inc., 630 Municipal Dr, Suite 300, Nazareth, PA 18064  
Tel: (610) 746 7081; Fax: (610) 743 8654  
Email: sales-us@u-pol.com Website: www.u-pol.com